

System 11

Textured Coating for Walls and Floors



The textured coating offers the possibility to create harmonious surfaces even on uneven ground. It convinces with a high mechanical surface load capacity. The jointless coating is hygienic, easy to maintain and is used e.g. in agriculture for silos, cattle and horse stables. It is an excellent alternative to tiles for swimming pools, showers and toilet facilities and has an attractive appearance. The coating is also suitable for use in stadiums.

System features:

- Seamless
- Hygienic
- Strong wall insulation
- Dirt-repellent
- Scratch-resistant
- Chemical resistant
- UV resistant - no yellowing
- Easy to clean
- Slip resistance for floors as required R9 - R13



Sealing **0,3 kg/sqm**
WILLPUR 2212 R solvent-free – 2-components
WILLPUR 2231 contains solvents – 2-components

Coating **0,6 kg/sqm**
WILLPOX 2134 – 2-components

Primer **0,5 kg/sqm**
WILLPOX 1115 – 2-components

Color options

Available in all RAL colors.



System 11

Textured Coating for Walls and Floors



Suitable for the following substrates:

<input checked="" type="checkbox"/> Concrete	<input checked="" type="checkbox"/> Screed	<input type="checkbox"/> Exposed aggregate concrete
<input type="checkbox"/> Asphalt	<input type="checkbox"/> Bitumen	<input checked="" type="checkbox"/> Laminate/PVC
<input checked="" type="checkbox"/> Tiles	<input checked="" type="checkbox"/> Wood	<input type="checkbox"/> Glass
<input checked="" type="checkbox"/> Ferrous metals	<input type="checkbox"/> Other metals	<input checked="" type="checkbox"/> Rigips

Total coating thickness	1-2 mm
Accessibility	1 day after the last working cycle
Working time	10 hours (for 100sqm)
No. of applications	3
Shore Hardness	Shore D83
Solvent-free	yes
Permeable	no
Water-permeable	no
Emission-free	yes

Tools



Mixing bucket



Mixing tool



Sealing roller



Tooth spatula



Structure roller

Processing information

When processing reactive plastics, the temperature of the substrate as well as the ambient temperature are of particular importance. At low temperatures, chemical reactions are generally delayed, which leads to an extended processing, reworkability, walkability and hardening time. At the same time, the material consumption increases due to the higher viscosity. At high temperatures, the chemical reactions are accelerated, which means that the above mentioned times can be shorter. For a complete hardening of the reaction plastic, the average temperature of the substrate must be above the minimum temperature.

More detailed processing instructions can be found in the system data sheets and the technical data sheets of the individual components! These are delivered with your goods.